# REACTION TO FIRE CLASSIFICATION REPORT
# IN ACCORDANCE WITH EN 13501-1:2018

**Contract no. 02849/23/Z00NZP**

| | |
|---|---|
| **Sponsor:** | **naturheld GmbH**<br>**Zur Betzenmühle 1**<br>**D-95703 Plößberg / OPf.** |
| **Prepared by:** | **Building Research Institute; 1, Filtrowa str.**<br>**00-611  Warszawa, Poland** |
| **Product name:** | **In-situ formed loose fill wood fiber insulation material naturheld GmbH (dry application)** |
| **Classification report №:** | **02849/23/Z00NZP/B/E replaces classification report No. 02849/23/Z00NZP issued on 26.01.2024** |
| **Issue number:** | **1** |
| **Date of issue:** | **15.03.2024** |

This classification report consists of 3 pages and may only be used or reproduced in its entirety.

## 1.    Introduction

This classification report defines the classification assigned to in-situ formed loose fill wood fibre insulation material naturheld GmbH (dry application) in accordance with the procedures given in EN 13501-1:2018.

## 2.    Details of classified product

### 2.1    General

In-situ formed loose fill cellulose fibre insulation material naturheld GmbH (dry application).

### 2.2    Product description

The product, is described below (according to Producer declaration).

Density range: approx. 38 kg/m$^3$
Loose fill insulation material made from cellulose fiber treated with fire protective additive with composition of fire protective additive is known by ITB
The product is designated to be applied dry.

## 3.   Test reports & test results in support of classification

### 3.1  Test reports

| Name of laboratory | Name of sponsor | Test report № | Test method |
|---|---|---|---|
| Fire Research Laboratory Building Research Institute | naturheld GmbH | LZP01-02849/23/Z00NZP | PN-EN 13823+A1:2022-12 |
| | | LZP02-02849/23/Z00NZP | PN-EN ISO 11925-2:2020 |

B A D A N I A  |  O P I N I E  |  E K S P E R T Y Z Y

00-611 Warszawa, ul. Filtrowa 1, tel. (22) 825 04 71, e-mail: instytut@itb.pl          **www.itb.pl**

## 3.2 Test results

| Test method | Parameter | Number of tests | Results | |
|---|---|---|---|---|
| | | | Continuous parameter – mean (m) | Compliance with parameters |
| PN-EN 13823+A1: 2022-12 In-situ formed loose fill wood fibre insulation material naturheld GmbH (dry application) with fire protective additive Density: 38 kg/m$^3$ Ref. LZP01-02849/23/Z00NZP Insulation thickness: 180 mm | $FIGRA_{0,2MJ}$ | 3 | 45,2 | (−) |
| | $FIGRA_{0,4MJ}$ | | 44,9 | (−) |
| | LFS < edge | | (−) | Y |
| | $THR_{600s}$ [MJ] | | 5,8 | (−) |
| | SMOGRA [$m^2/s^2$] | | 10,5 | (−) |
| | $TSP_{600s}$ [$m^2$] | | 152,9 | (−) |
| | Flaming droplets/particles | | (-) | N |
| PN-EN ISO 11925-2: 2020 Surface and edge on front exposure Exposure time 30 s Density: 38 kg/m$^3$ Ref. LZP02-02849/23/Z00NZP | $F_s$ ≤150 mm | 6 | (−) | Y |
| | Flaming Droplets/particles | | (−) | N |
| (−): not applicable, Y: Yes, N: No | | | | |

## 4 Classification and field of application

### 4.1 Reference of classification

This classification has been carried out in accordance with EN 13501-1:2018.

### 4.2 Classification

The product, the in-situ formed loose fill wood fiber insulation material naturheld GmbH (dry application), in relation to its reaction to fire behaviour is classified:

**B**

The additional classification in relation to smoke production is:

**s2**

The additional classification in relation to flaming droplets/particles is:

**d0**

The format of the reaction to fire classification for construction products excluding floorings and linear pipe thermal insulation products is:

| Fire behaviour | | Smoke production | | | Flaming droplets | |
|---|---|---|---|---|---|---|
| **B** | **-** | **s** | **2** | **,** | **d** | **0** |

**i.e.: B-s2,d0**

## Reaction to fire classification: B-s2,d0

### 4.3 Field of application

This classification is valid for the product described in point 2 this classification report and
 following substrates, air gaps and variation in product parameters:
- Acc. to EN 15101-1 Annex C Table C.4 results are valid for any end-use substrates with the minimum fire classifications D-s3, d0
- density range of the insulation – 38 kg/m$^3$ ± 15%
-possible thickness range: no limitation
- fixing method – no limitation
- no variation in fire retardant composition allowed

## 5    Limitations

This classification given remains valid as long as:
- Test method remains unchanged.
- Product standard or technical assessment remains unchanged.
- Constructional or material modifications do not exceed limits of the field of application defined in 4.3.
This classification report has been issued in electronic form, with qualified electronic signatures of persons responsible. A printout of this report is not an original document.
This classification document does not represent type assessment or certification of the product.

|  | **Signed*** | **Approved*** |
|---|---|---|
| Prepared: |  |  |
|  | electronic sigNaturs | electronic sigNaturs |
| Verified: |  |  |
|  | electronic sigNaturs |  |

* - For and on behalf of "Name of the organisation"